

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 2002-180203

(43)Date of publication of application : 26.06.2002

(51)Int.Cl. C22C 38/00
 C21D 1/06
 C21D 6/00
 C22C 38/58
 F16C 19/44
 F16C 33/34
 F16C 33/62
 F16C 33/64

(21)Application number : 2000-378512

(71)Applicant : NTN CORP

(22)Date of filing : 13.12.2000


(72)Inventor : TANAKA HIROMASA

(54) NEEDLE BEARING COMPONENTS, AND METHOD FOR PRODUCING THE COMPONENTS

(57)Abstract:

PROBLEM TO BE SOLVED: To provide needle roller bearing components in which a long endurance life can be secured even under atmospheric conditions where sliding contact occurs, and the temperature is made high, and to provide a method for producing the components.

SOLUTION: The needle roller bearing components consists of steel at least containing, as alloy elements in the base, by mass, 0.1 to 0.4% C, 0.3 to 3.0% Si, 0.2 to 2.0% Mn, $\leq 0.03\%$ P, $\leq 0.03\%$ S, 0.3 to $< 2.5\%$ Cr, 0.1 to $< 2.0\%$ Ni, $\leq 0.050\%$ Al, $\leq 0.003\%$ Ti, $\leq 0.0015\%$ O and $\leq 0.025\%$ N, and the balance Fe with inevitable impurities. The steel is subjected to quenching and tempering treatment after carburizing or carbo-nitriding treatment.



LEGAL STATUS

[Date of request for examination]

24.09.2004

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision]

1001907

(19) 日本国特許庁 (J P)

(12) 公開特許公報 (A)

(11) 特許出願公開番号

特開2002-180203

(P2002-180203A)

(43) 公開日 平成14年6月26日 (2002. 6. 26)

(51) Int. Cl. ⁷	識別記号	F I	タームコード (参考)	
C 2 2 C 38/00	3 0 1	C 2 2 C 38/00	3 0 1 Z	3 J 1 0 1
C 2 1 D 1/06		C 2 1 D 1/06	A	
6/00		6/00	K	
			D	
			W	

審査請求 未請求 請求項の数 6 O L (全 10 頁) 最終頁に続く

(21) 出願番号 特願2000-378512(P2000-378512)

(22) 出願日 平成12年12月13日 (2000. 12. 13)

(71) 出願人 000102692

エヌティエヌ株式会社

大阪府大阪市西区京町堀 1 丁目 3 番 17 号

(72) 発明者 田中 広政

三重県桑名市大宇東方字尾弓田3066 エヌ

ティエヌ株式会社内

(74) 代理人 100064746

弁理士 深見 久郎 (外 3 名)

F ターム (参考) 3J101 AA14 AA24 BA10 BA50 BA70

DA02 DA03 EA02 FA31

(54) 【発明の名称】 針状ころ軸受構成部品およびその製造方法

(57) 【要約】

【課題】 すべり接触が生じ、かつ高温となる雰囲気条件下でも長い耐久寿命を確保できる針状ころ軸受構成部品およびその製造方法を提供する。

【解決手段】 本発明の針状ころ軸受構成部品は、素地中に合金元素として質量%で、Cを0.1%以上0.4%以下、Siを0.3%以上3.0%以下、Mnを0.2%以上2.0%以下、Pを0.03%以下、Sを0.03%以下、Crを0.3%以上2.5%未満、Niを0.1%以上2.0%未満、Alを0.050%以下、Tiを0.003%以下、Oを0.0015%以下、Nを0.025%以下で少なくとも含み、残部がFeおよび不可避不純物からなる鋼材よりなり、浸炭・浸炭窒化処理後に焼入れ焼戻し処理された構成を有する。

